



Rubberized Cork Sheet TF8810

| GradeTF8810 | Specification | Typical Result * | Test Method |
|---|--|--|------------------------------|
| Binder | Synthetic Rubber/NBR | Synthetic Rubber/NBR | As per IS:4253(Part II) 2008 |
| Cork Grain Size | 0.5 – 1.0 MM I | 0.5 -1.0MM | |
| Physical Characteristics Hardness, Shore A..... | 75 ~ 85 | 79 | |
| Compressibility at400 PSI(%)..... | 15~ 25 | 20.41 | |
| Recovery after (%)..... | 75, min | 82.16 | |
| Tensile Strength (KgF/cm2)..... | 19, min | 30.86 | |
| Flexibility (Thickness X 3) Specific Gravity (gm/cc) Compression Set (%) Side Flow (%) | NO cracks 0.70 ~ 0.90 90 Max 18 Max | NO cracks 0.81 78.91 Not done | |
| Volume Change After Immersion ASTM no.1 Oil, 70 hrs @100deg C(%). ASTM no.3 Oil, 70 hrs @100deg C(%). | -15..+ 5 10 % max | - 2.40 6.54 | |

*The results are based on typical samples tested in our lab. Due to the flexible and highly compressible nature of product, the results may vary at customers end.

**SPECIFICATION AND TEST METHODS ACCORDING TO: -
IS: 4253 (Part - 2)1980**

Date of issue: 06-07-2009

Revision No: 03

Date: 06- Feb.- 2012