

ID Material: R. Antich Revision: 5 Date: 6/27/18

TF2666

TF2666 is developed for static applications, it is rigid and moulded friction material. Its most noted characteristics are hardness, mechanical strength and resistance to temperature. Its co efficiency is very high. It is composed basically of resins and rubber as a link system with friction modifying agents. The mineral fibres enhance the strength which helps to establish the friction value. ST06 is fully cured and suitable for bonding and riveting.

Material Data

Friction Properties (according to graphics)

Static Friction Coefficient (15bar, from box): 0.40±0.05 ц Static Friction Coefficient (15bar, 100oC): 0.43±0.05 μ Dynamic Friction Coefficient (10bar, 10m/s): 0.40±0.05 Wear Rate (10bar, 15m/s): 100±10 mm3/Kwh To Fading (10bar, 10m/s): >662

Material Type: Rigid material

Appearance / Formats









Physical Properties

Hardness (DIN53505): 83±5 Shore-D Specific Gravity (ASTM D792-91): 1.80±0.05 gr/cm3

Applications

Callipers for industrial applications - Damper Technologies - Forging machinery - Heavy duty static applications - Holding Mechanical Structures - Punch-die press blocks - Static brakes - Yaw brakes -

Mechanical Properties

Tensile Strength (ASTM D638-10): 23±5 N/mm² 120±5 N/mm² Compressive Strength (UNE 53205): **Poisson Coefficient:** 0.24±0.03 Young Modulus (ASTMD 638-10): 9190±100 N/mm² Price Level: \$\$\$\$

Compliance Reach (EC) 1907/2006 - RoHS 2011/65/EU:

Others


Perlitic cast iron, hardness **Recommended Mating Surface:**

HB150-200

Recommended Working Values

T° Max. Continuous Operation: 482 °F T° Max. Intermittent Operation: 662 °F **Recommended Adhesives:** Thermosetting adhesive

The above data is taken from specific test parameters therefore results can vary in different application conditions



Rubbing speed, temperature and pressure are related. Changing any values will change other. The values shown represent typical conditions, but are not ultimate limits of the material.